

06/24/98

Jc504 U.S. PTO

Please type a plus sign (+) inside this box → ☒Approved for use through 09/30/2000. OMB 0654-0037
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**UTILITY
PATENT APPLICATION
TRANSMITTAL**

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Attorney Docket No.

97-2301

First Inventor or Application Identifier

R10JA

Title

Aluminum-Copper-Magnesium

Express Mail Label No.

EH 423664208 US

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

1. ☒ * Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
2. ☒ Specification [Total Pages 20]
(preferred arrangement set forth below)
- Descriptive title of the invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☒ Drawing(s) (35 U.S.C. 113) [Total Sheets 10]
4. Oath or Declaration [Total Pages 30]
- a. ☐ Newly executed (original or copy)
 - b. ☐ Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 17 completed)
(Note Box 5 below)
 - i. ☐ **DELETION OF INVENTOR(S)**
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).
5. ☐ Incorporation By Reference (useable if Box 4b is checked)
The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b, is considered to be part of the disclosure of the accompanying application and is hereby incorporated by reference therein.

ADDRESS TO:Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

6. ☐ Microfiche Computer Program (Appendix)
7. Nucleotide and/or Amino Acid Sequence Submission
(if applicable, all necessary)
- a. ☐ Computer Readable Copy
 - b. ☐ Paper Copy (identical to computer copy)
 - c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

8. ☐ Assignment Papers (cover sheet & document(s))
9. ☐ 37 C.F.R. § 3.73(b) Statement ☐ Power of Attorney
(when there is an assignee)
10. ☐ English Translation Document (if applicable)
11. ☒ Information Disclosure Statement (IDS)/PTO-1449 ☒ Copies of IDS Citations
12. ☐ Preliminary Amendment
13. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
- * Small Entity
14. ☐ Statement(s) ☐ Status filed in prior application, Status still proper and desired
(PTO/SB/09-12)
15. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
16. ☒ Other: UNSIGNED...DECLARATION

* NOTE FOR ITEMS 1 & 14: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).

17. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP)

of prior application No: _____

Prior application information: Examiner _____

Group / Art Unit: _____

18. CORRESPONDENCE ADDRESS☐ Customer Number or Bar Code Label

(Insert Customer No. or Attach bar code label here)

or ☒ Correspondence address below

Name	CHARLES Q. BUCKWALTER, ESQ.				
Address	Aluminum Company of America ATC-100 Technical Drive				
City	Alcoa Center	State	PA	Zip Code	15067-0001
Country	U.S.A.	Telephone	(724) 337-	Fax	(724) 337-5959

Name (Print/Type)

CHARLES Q. BUCKWALTER

Registration No. (Attorney/Agent)

Signature

Charles Q. Buckwalter

Date

6/24/98

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

FEE TRANSMITTAL

Patent fees are subject to annual revision on October 1.

These are the fees effective October 1, 1997.

Small Entity payments must be supported by a small entity statement, otherwise large entity fees must be paid. See Forms PTO/SB/09-12. See 37 C.F.R. §§ 1.27 and 1.28.

TOTAL AMOUNT OF PAYMENT (\$) **900****Complete if Known**

Application Number

Filing Date

First Named Inventor **RIOJA**

Examiner Name

Group / Art Unit

Attorney Docket No. **97-2301****METHOD OF PAYMENT (check one)**

- 1.
- ☒
- The Commissioner is hereby authorized to charge indicated fees and credit any over payments to:

Deposit Account Number
Deposit Account Name**01-1000****Aluminum Co. of America**

- ☒
- Charge Any Additional Fee Required Under 37 C.F.R. §§ 1.16 and 1.17
- ☐
- Charge the Issue Fee Set in 37 C.F.R. § 1.18 at the Mailing of the Notice of Allowance

- 2.
- ☐
- Payment Enclosed:

☐ Check ☐ Money Order ☐ Other**FEE CALCULATION****1. BASIC FILING FEE**

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
101 790	201 395	Utility filing fee	790
106 330	206 165	Design filing fee	
107 540	207 270	Plant filing fee	
108 790	208 395	Reissue filing fee	
114 150	214 75	Provisional filing fee	

SUBTOTAL (1) (\$) **790****2. EXTRA CLAIM FEES**

Total Claims	Extra Claims	Fee from below	Fee Paid
25	20** = 5	22	110
Independent Claims	2	3** = 0	82
Multiple Dependent		270	

**or number previously paid, if greater; For Reissues, see below

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description
103 22	203 11	Claims in excess of 20
102 82	202 41	Independent claims in excess of 3
104 270	204 135	Multiple dependent claim, if not paid
109 82	209 41	** Reissue independent claims over original patent
110 22	210 11	** Reissue claims in excess of 20 and over original patent

SUBTOTAL (2) (\$) **110****FEE CALCULATION (continued)****3. ADDITIONAL FEES**

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
105 130	205 65	Surcharge - late filing fee or oath	
127 50	227 25	Surcharge - late provisional filing fee or cover sheet	
139 130	139 130	Non-English specification	
147 2,520	147 2,520	For filing a request for reexamination	
112 920*	112 920*	Requesting publication of SIR prior to Examiner action	
113 1,840*	113 1,840*	Requesting publication of SIR after Examiner action	
115 110	215 55	Extension for reply within first month	
116 400	216 200	Extension for reply within second month	
117 950	217 475	Extension for reply within third month	
118 1,510	218 755	Extension for reply within fourth month	
128 2,060	228 1,030	Extension for reply within fifth month	
119 310	219 155	Notice of Appeal	
120 310	220 155	Filing a brief in support of an appeal	
121 270	221 135	Request for oral hearing	
138 1,510	138 1,510	Petition to institute a public use proceeding	
140 110	240 55	Petition to revive - unavoidable	
141 1,320	241 660	Petition to revive - unintentional	
142 1,320	242 660	Utility issue fee (or reissue)	
143 450	243 225	Design issue fee	
144 670	244 335	Plant issue fee	
122 130	122 130	Petitions to the Commissioner	
123 50	123 50	Petitions related to provisional applications	
126 240	126 240	Submission of Information Disclosure Stmt	
581 40	581 40	Recording each patent assignment per property (times number of properties)	
146 790	246 395	Filing a submission after final rejection (37 CFR 1.129(a))	
149 790	249 395	For each additional invention to be examined (37 CFR 1.129(b))	
Other fee (specify) _____			
Other fee (specify) _____			

* Reduced by Basic Filing Fee Paid

SUBTOTAL (3) (\$) **900****SUBMITTED BY**

Typed or Printed Name

CHARLES Q BUCKWALTER

Signature

Charles Q Buckwalter

Date

6/24/98**Complete (if applicable)**

Reg. Number

32969

Deposit Account User ID

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

***ALUMINUM-COPPER-MAGNESIUM ALLOYS HAVING
ANCILLARY ADDITIONS OF LITHIUM***

BACKGROUND OF THE INVENTION

This invention relates to aluminum-copper-magnesium alloys having ancillary additions of lithium in order to decrease density while at the same time increasing strength, toughness, and especially fatigue crack growth resistance of the aluminum-copper-magnesium alloy. These alloys are useful in aerospace applications, for example.

It is generally well known in the aerospace industry that one of the most effective ways to reduce the weight of an aircraft is to reduce the density of aluminum alloys used in aircraft construction. This desire led to the addition of lithium, the lowest density metal element, to aluminum alloys. Aluminum Association ("AA") alloys, such as 2090 and 2091 contained about 2.0 wt % lithium, which translated into about a 7% weight savings over alloys containing no lithium. Another aluminum alloy, AA 8090 contained about 2.5 wt % lithium, which translated into an almost 10% weight savings over alloys without lithium.

Molten lithium, however, is a highly reactive and highly aggressive material, which is difficult to handle and which is also difficult to alloy with the base alloy. Because of its high reactivity, any moisture in the presence of the molten aluminum-lithium can cause explosions. In addition, because of its highly aggressive nature, special refractories must be used in casting the lithium alloys.

Because the propensity for explosions of molten aluminum-lithium is reduced as the weight percent of lithium is reduced, it is desired to reduce lithium levels. However, it is also desirable to maintain the properties of less density, greater strength and increased fatigue crack growth

resistance at the same time. Of course, it was known that reductions in the weight percent of lithium would result in less weight savings, but this tradeoff was made in order to reduce the difficulty of making the aluminum-lithium alloys.

5 United States Patent No. 5,455,003 discloses aluminum-copper-lithium alloys with improved cryogenic fracture toughness. Of major importance in cryogenic applications are high strength and high fracture toughness. These properties are obtained by artificially aging the
10 aluminum alloy. However, this aging will have a detrimental effect on fatigue crack growth resistance. In damage tolerant applications in aircraft, fatigue crack growth resistance is very important. Better fatigue crack growth resistance means that cracks will grow slower, thus making airplanes much safer
15 because small cracks can be detected before they achieve critical size for catastrophic propagation. Furthermore, slower crack growth can have an economic benefit due to the fact that longer inspection intervals can be utilized.

What is needed, therefore, is an aluminum alloy
20 useful for, among other things, damage tolerant applications in aircraft which has not only low density, high strength and good fracture toughness, but also excellent fatigue crack growth resistance.

SUMMARY OF THE INVENTION

25 The aluminum alloy of the invention has met or exceeded the above-mentioned needs as well as others. The aluminum alloy comprises up to about 4.5 wt % copper; from about 0.6 to 6.0 wt % magnesium; and from about 0.01 to 1.0 wt % lithium. It has been found, quite surprisingly
30 and unexpectedly, that the ancillary additions of low levels of lithium to aluminum-copper-magnesium alloys provided a high strength, low density material that exhibited good fracture toughness and improved fatigue crack growth resistance over prior art aluminum-copper-magnesium alloys.

BRIEF DESCRIPTION OF THE DRAWINGS

A full understanding of the invention can be gained from the following detailed description of the invention when read in conjunction with the accompanying drawings in which:

5 Figure 1A is a graph showing the composition space covering aluminum-copper-magnesium alloys with ancillary lithium additions.

10 Figure 1B is a chart showing the tensile yield strength of various specimens made from aluminum alloys containing aluminum-copper-magnesium alloys designated Alloy A, Alloy B, Alloy C and Alloy D after being subjected to different aging conditions.

15 Figure 2 is a bar graph showing the improvement in specific strength for some of the specimens shown in Figure 1.

 Figure 3 is a graph showing the typical representation of fatigue crack growth performance rate da/dn (in/cycle) and how it changes with performance improvements.

20 Figure 4 is a graph showing the fatigue crack growth curves for (1) Alloy A-T3 plate; (2) Alloy C-T3 plate; and (3) Alloy D-T3 plate.

 Figure 5 is a graph showing the fatigue crack growth curves for (1) Alloy A-T39 plate; (2) Alloy C-T39 plate; and (3) Alloy D-T39 plate.

25 Figure 6 is a graph showing the fatigue growth curves for (1) Alloy A-T8 plate; (2) Alloy C-T8 plate; and (3) Alloy D-T8 plate.

 Figure 7 is a bar graph showing the percentage change in da/dn at $\Delta K = 10 \text{ Ksi (in)}^{1/2}$.

30 Figure 8 is a graph showing the fracture toughness R-curves of Alloy A-T3 and Alloy C-T3.

 Figure 9 is a graph showing the fracture toughness R-curves of Alloy A-T39, Alloy C-T39 and Alloy D-T39 plate.

DETAILED DESCRIPTION

For the description of alloy compositions that follow, all references are to weight percentages (wt %) unless otherwise indicated. When referring to any numerical range of values, such ranges are to be understood to include each and every number and/or fraction between the stated range minimum and maximum. A range of about 0.01 to 0.99 wt % lithium, for example, would include all intermediate values of about 0.02, 0.03, 0.04 and 0.1 wt % all the way up to and including .97, .98 and .9895 wt % lithium. The same applies to the other elemental ranges set forth below. The term "*substantially free*" means having no significant amount of that component purposely added to the alloy composition, it being understood that trace amounts of incidental elements and/or impurities may find their way into a desired end product.

As used herein, the term "*damage tolerant aircraft part*" means any aircraft or aerospace part which is designed to ensure that its crack growth life is greater than any accumulation of service loads which could drive a crack to a critical size resulting in catastrophic failure. Damage tolerance design is used for most of the primary structure in a transport category airframe, including but not limited to fuselage panels, wing boxes, horizontal and vertical stabilizer boxes, pressure bulkheads, and door and window frames. In inspectable areas, damage tolerance is typically achieved by redundant designs for which the inspection intervals are set to provide at least two inspections per number of flights or flight hours it would take a visually detectable crack to grow to its critical size.

The present invention relates to an aluminum-copper-magnesium alloy having ancillary additions of lithium. In accordance with the invention, a wrought aluminum-copper-magnesium-lithium alloy is provided which has improved strength, fracture toughness and fatigue crack growth

resistance over prior art aluminum-copper-magnesium alloys. The alloys of the present invention are especially useful for damage tolerant aircraft parts, such as lower wing sections, because of the surprising and unexpected increase in fatigue crack growth resistance over prior art aluminum-copper-magnesium alloys. Because of the addition of low levels of lithium additions, the problems of higher (*i.e.*, over 1.5 wt % *lithium*) additions of lithium, such as explosions of the molten metal, are reduced or eliminated.

The compositional ranges of the main alloying elements (*copper, magnesium and lithium*) of the improved alloy of the invention are broadly defined as follows: (1) up to 4.5 wt % copper; (2) from about .6 to 6.0 wt % magnesium; and (3) from about 0.01 to 0.99 wt % of lithium. The balance of the aluminum alloy of the invention contains aluminum and incidental impurities.

In addition to aluminum, copper, magnesium and lithium, the alloys of the present invention can contain dispersoids selected from the group consisting of chromium, vanadium, titanium and zirconium and mixtures thereof in the range of about 0.0 to 0.6 wt % and/or dispersoids such as manganese, nickel, iron, hafnium and scandium and mixtures thereof in the range of 0 to 1 wt %. Other alloying elements, such as zinc, silver and silicon and mixtures thereof in amounts up to about 2.0 wt % can also be added.

The copper is added to increase the strength of the aluminum base alloy. Care must be taken, however, to not add too much copper since the corrosion resistance can be reduced. Also, copper additions beyond maximum solubility can lead to low fracture toughness and low damage tolerance.

The magnesium is added to provide strength and reduce density. Care should be taken, however, to not add too much magnesium since magnesium additions beyond maximum solubility will lead to low fracture toughness and low damage tolerance.

The lithium is added to reduce density and to increase strength. Care should be taken, however, in not adding too much lithium since exceeding the maximum solubility will lead to low fracture toughness and low damage tolerances.

- 5 Lithium additions in amounts of about 1.5 wt % and above result in the formation of the δ' ("delta prime") phase with composition of Al_3Li . The presence of this phase, Al_3Li , is to be avoided in the alloys of the present invention.

- 10 The interaction of lithium atoms in supersaturated solid solution, with atoms of magnesium and/or copper appear to give rise to the formation of clusters of atoms of solute. This behavior is observed by the appearance of diffuse scatter in electron diffraction images. This behavior, which was not expected and is surprising, is apparently responsible for the
15 improvements in fatigue performance of the alloys of the invention, which will be discussed below.

- It has been found, quite unexpectedly and surprisingly, that the combination of lower copper levels, higher magnesium levels and lower levels of lithium give a
20 surprisingly strong, less dense aluminum alloy which has superior fatigue crack growth resistance. Fatigue crack growth resistance is a critical property for damage tolerant aircraft parts, such as fuselage sections and lower wing sections. As is known, these parts of an aircraft are subject
25 to cyclical stresses, such as the fuselage skin which is expanded and contracted upon pressurization and depressurization of the aircraft cabin and the lower wing skin which experiences tensile stresses in flight and compressive stresses while the aircraft is on the ground. Improved
30 fatigue crack growth resistance means cracks will grow and reach their critical dimension more slowly. This allows longer inspection intervals to be used, thus reducing aircraft operating cost. Alternatively, the applied stress could be raised while keeping the same inspection interval, thereby
35 reducing aircraft weight.

Returning now to a discussion of the alloy composition of the invention, it should be noted that the copper and magnesium in the compositional ranges set forth above will be soluble in the alloy. This is important in that atoms of the alloying elements in solid solution or forming clusters translate to increased fatigue crack growth resistance, which is, as was mentioned above, a critical property for damage tolerant aircraft parts.

Referring now to Figure 1A, the broad, preferred, more preferred and most preferred ranges for the copper and magnesium contents of the aluminum alloy of the invention will be discussed. For all of these copper and magnesium ranges, the range of the lithium content is from about 0.01 to 0.99 wt %. A benefit has been observed when the lithium concentration is above 0.25 and even 0.35 and up to 0.95. The lithium concentration will vary depending on the desired level of improved performance of the wrought product. The combination of copper, magnesium and lithium needs to be carefully considered as to not exceed maximum solubility. The following composition ranges were selected using a combination of phase diagram data from thermodynamic equilibrium and experimental results.

Turning now to Figure 1A, it can be seen that the broad ranges for copper and magnesium fall within a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, the closed area being bounded by generally straight lines joining the following points:

POINT A = 0 Cu, 0.6 Mg
POINT B = 4.5 Cu, 0.6 Mg
POINT C = 4.5 Cu, 6.0 Mg
POINT D = 0 Cu, 6.0 Mg
and back to POINT A.

The preferred ranges for copper and magnesium are defined by a closed area on a graph with wt % copper on the x-axis and

wt % magnesium on the y-axis, the closed area being bounded by generally straight lines joining the following points:

5 POINT A = 0 Cu, 0.6 Mg
 POINT B = 4.5 Cu, 0.6 Mg
 POINT E = 4.5 Cu, 2.3 Mg
 POINT F = 2.0 Cu, 6.0 Mg
 POINT D = 0 Cu, 6.0 Mg
 and back to POINT A.

10 The more preferred ranges for copper and magnesium are defined by a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, the closed area being bounded by generally straight lines joining the following points:

15 POINT A - 0 Cu, 0.6 Mg
 POINT B = 4.5 Cu, 0.6 Mg
 POINT G = 1.5 Cu, 6.0 Mg
 POINT D = 0 Cu, 6.0 Mg
 and back to POINT A.

20 Finally, the most preferred ranges for copper and magnesium are defined by a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, the closed area being bounded by generally straight lines joining the following points:

25 POINT A = 0 Cu, 0.6 Mg
 POINT B = 4.5 Cu, 0.6 Mg
 POINT H = 4.5 Cu, 2.0 Mg
 POINT I = 0 Cu, 2.0 Mg
 and back to POINT A.

30 It will be appreciated that the equation for straight line 1 on Figure 1A (between Points E and F) can be expressed as follows:

$$Cu = \frac{-2.5}{3.7}(Mg-6)+2$$

and the equation for straight line 2 (between Points B and G) can be expressed as the following equation:

$$Cu = \frac{-3}{5.4}(Mg-6) + 1.5$$

5 The following example sets forth alloys and resulting wrought products made in accordance with the invention.

EXAMPLE

10 An ingot of an aluminum-copper-magnesium alloy having the following composition was cast:

INGOT NO. 1

<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Zn</u>	<u>Zr</u>
0.03	0.03	3.24	0.58	1.32	-0-	0.11

15 (Remainder is aluminum and incidental impurities.)

Material fabricated from this ingot will be designated Alloy A hereinafter in this Example.

20 After this, the remaining molten metal was re-alloyed (i.e., alloying again an alloy already made) by adding 0.25% lithium to create a target addition of 0.25 wt % lithium. A second ingot was then cast having the following composition:

INGOT NO. 2

25

<u>Li</u>	<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Zn</u>	<u>Zr</u>
0.19	0.03	0.04	3.41	0.61	1.28	-0-	0.1

(Remainder is aluminum and incidental impurities.)

Material fabricated from this ingot will be designated Alloy B hereinafter in this Example.

064290 " EET 0160

Ingot No. 3 was created by re-alloying the remaining molten metal after casting Ingot No. 2 and then adding another 0.25 wt % lithium to create a total target addition of 0.50 wt % lithium. Ingot No. 3 had the following composition:

5 INGOT NO. 3

<u>Li</u>	<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Zn</u>	<u>Zr</u>
0.35	0.04	0.04	3.37	0.6	1.2	-0-	0.11

(Remainder is aluminum and incidental impurities.)

- 10 Material fabricated from this ingot will be designated Alloy C hereinafter in this Example.

Ingot No. 4 was created by re-alloying the remaining molten metal after casting Ingot No. 3 and then adding another 0.25 wt % lithium to create a total target addition of 0.75 wt % lithium. A fourth ingot was cast having the following composition:

15 INGOT NO. 4

<u>Li</u>	<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Zn</u>	<u>Zr</u>
0.74	0.02	0.03	3.34	0.56	1.35	0.01	0.12

20

(Remainder is aluminum and incidental impurities.)

Material fabricated from this ingot will be designated Alloy D hereinafter in this Example.

- 25 The four ingots were stress relieved and homogenized. The ingots were then subjected to a standard presoak treatment after which the ingots were machine scalped. The scalped ingots were then hot rolled into four (4) separate 0.7 inch gauge plates using hot rolling practices typical of 2XXX alloys.

- 30 After the four (4) separate plates were produced, a section of each of the plates was removed. Each of the four (4) sections were (a) solution heat treated; (b) quenched; and (c) stretched 1.5%. After this, eight (8) tensile strength test samples were produced from each of the

004250-224066

5 treated four (4) sections, making a total of thirty-two (32) tensile strength test samples. One tensile strength test sample from each group of eight (8) (there being a total of four (4) plates in each group) was each subject to eight (8) different aging conditions, as described in the legend of Figure 1. After this, tensile yield strength tests were performed, with the results being shown in Figure 1B. It will be seen that the alloys having lithium additions exhibited greater strength than those without lithium, while at the same time exhibiting thermal stability.

10 After this, the remainder of three of the four plates (i.e., Ingot No. 1 plate, Ingot No. 3 plate and Ingot No. 4 plate) was each cut into thirds (1/3rds), to form pieces 1, 2 and 3 for each plate, or a total of 9 pieces. 15 Piece 1 of all three plates were (a) solution heat treated; (b) quenched; (c) stretched 1 1/2%; and (d) aged to T8 temper by aging it 24 hours @ 350°F. These pieces were designated Alloy A-T8; Alloy C-T8; and Alloy D-T8. Piece 2 of all three plates were (a) solution heat treated; (b) quenched; 20 (c) stretched 1 1/2%; and (d) naturally aged to T3 temper. These pieces were designated Alloy A-T3; Alloy C-T3; and Alloy D-T3. Finally, Piece 3 of all three plates were (a) solution heat treated; (b) quenched; (c) cold rolled 9%; (d) stretched 1 1/2%; and (e) naturally aged. These pieces 25 were designated Alloy A-T39; Alloy C-T39; and Alloy D-T39. It was these pieces which provided the material for all of the further testing which will be reported herein.

Referring now to Figure 2, the tensile yield strength divided by density for a testing portion of each of the nine (9) pieces produced above is shown. It can be seen that improvements in the tensile yield strength to density ratio were found for ancillary lithium additions.

Referring now to Figures 3-7, the key property of fatigue crack growth resistance will now be discussed. 35 Figure 3 is a graph showing the typical representation of

fatigue crack growth performance and how improvements therein can be shown. The x-axis of the graph shows the applied driving force for fatigue crack propagation in terms of the stress intensity factor range, ΔK , which is a function of applied stress, crack length and part geometry. The y-axis of the graph shows the material's resistance to the applied driving force and is given in terms of the rate at which a crack propagates, da/dn in inch/cycle. Both ΔK and da/dn are presented on logarithmic scales as is customary. Each curve represents a different alloy with the alloy having the curve to the right exhibiting improved fatigue crack growth resistance with respect to the alloy having the curve to the left. This is because the alloy having the curve to the right exhibits a slower crack propagation rate for a given ΔK which represents the driving force for crack propagation.

Turning to Figures 4-6, it can be seen, that based on the criteria discussed with respect to Figure 3, the addition of lithium substantially increases the fatigue crack growth resistance in the respective alloys in the T3 and T39 conditions. The fatigue crack rates for crack driving forces of ΔK equal to 10 Ksi (in)^{1/2} are summarized in Figure 7. The percentage improvement in fatigue crack growth resistance (i.e., percentage reduction in fatigue crack growth rates) is given at the top of the graph. Alloy C-T3 and Alloy D-T3 show improvements of 27% and 26%, respectively over Alloy A-T3 (no lithium additions). The percentage improvements in fatigue crack growth resistance of Alloy C-T39 and Alloy D-T39 over Alloy A-T39 (no lithium additions) was 67% and 47% respectively.

With regard to the T8 alloys, it can be seen that the lithium additions do not improve the fatigue crack growth resistance. In the case of artificially aged alloys, aged to peak strength, the only advantage of lithium additions is in terms of additional strength and lower density.

Figures 8 and 9 show the fracture toughness R-curves for the T3 and T39 tempers, respectively. The R-curve is a measure of resistance to fracture (K_R) versus stable crack extension (Δa_{eff}). In addition, the following table shows single-point measurements of fracture toughness for Alloys A, C and D in the T3, T39 and T8 tempers in terms of K_{R25} , which is the crack extension resistance, K_R , on the R-curve corresponding to the 25% secant offset of the test record of load versus crack-opening displacement (COD), and K_q , which is the crack extension resistance corresponding to the 5% secant offset of the test record of load versus COD. K_{R25} is an appropriate measure of fracture toughness for moderate strength, high toughness alloy/tempers such as T3 and T39, while K_q is appropriate for higher strength, lower toughness alloy/tempers such as T8.

TABLE
Strength And Toughness Measurements
(Tensile Longitudinal Properties - Toughness Orientation L-T)

	<u>Alloy/Temper</u>	<u>TYS (Ksi)</u>	<u>UTS (Ksi)</u>	<u>Elongation (%)</u>	<u>K_q (Ksi in^{1/2})</u>	<u>K_R 25 (Ksi in^{1/2})</u>
20	Alloy A-T3	47.7	65.6	18.6	-	97.9
	Alloy C-T3	51.4	69.8	17.1	-	107.8
	Alloy D-T3	51.1	70.6	17.5	-	NOT TESTED
	Alloy A-T39	61.2	67.3	11.4	-	88.8
25	Alloy C-T39	63.3	70.7	9.3	-	91.5
	Alloy D-T39	65.7	70.5	9.9	-	97.5
	Alloy A-T8	63.7	69.7	12.1	32.4	-
	Alloy C-T8	65.9	71.9	11.7	38.7	-
30	Alloy D-T8	67.8	73.8	10.7	38.9	-

It will be appreciated that fracture toughness is somewhat improved by the lithium additions. Moreover, it should be noted that lithium additions yielded improved toughness at a higher strength level. Therefore, the strength/toughness relationship was significantly improved.

WHAT IS CLAIMED IS:

1. An aluminum alloy comprising up to about 4.5 wt % copper, from about 0.6 to 6.0 wt % magnesium and from about 0.01 to 0.99 wt % lithium.
- 5 2. The aluminum alloy of Claim 1, wherein said lithium content is from about 0.25 to 0.99 wt %.
3. The aluminum alloy of Claim 2, wherein said lithium content is from about 0.25 to 0.95 wt %.
- 10 4. The aluminum alloy of Claim 3, wherein said lithium content is from about 0.35 to 0.95 wt %.
5. The aluminum alloy of Claim 1, including a dispersoid selected from the group consisting
15 of chromium, vanadium, titanium and zirconium and mixtures thereof in the amount of from about 0.0 to 0.6 wt %.
6. The aluminum alloy of Claim 1, including a dispersoid selected from the group consisting
20 of manganese, nickel, iron, hafnium, scandium and mixtures thereof in the amount of from about 0.0 to 1.0 wt %.
7. The aluminum alloy of Claim 1, including a first dispersoid selected from the group consisting of chromium, vanadium, titanium, zirconium and mixtures thereof in the amount of from about 0.0 to 0.6 wt %
25 and a second dispersoid selected from the group consisting of manganese, nickel, iron, hafnium, scandium and mixtures thereof in the amount of from about 0.04 to 1.0 wt %.

8. The aluminum alloy of Claim 1, including other alloying elements selected from the group consisting of zinc, silver, silicon and mixtures thereof in the amount of from about 0.0 to 2.0 wt %.

5 9. A damage tolerant aircraft part made from the alloy of Claim 1.

10. A fuselage section made from the alloy of Claim 1.

10 11. A lower wing section made from the alloy of Claim 1.

15 12. An aluminum alloy comprising copper, magnesium and lithium, the lithium content being from about 0.01 to 0.99 wt % and the copper and magnesium weight percent values falling within a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, said closed area being bounded by generally straight lines joining the following points:

20 POINT 1 = 0 Cu. 0.6 Mg
POINT 2 = 4.5 Cu, 0.6 Mg
POINT 3 = 4.5 Cu, 6.0 Mg
POINT 4 = 0 Cu, 6.0 Mg
and back to POINT 1.

25 13. The aluminum alloy of Claim 12, wherein the copper and magnesium weight percent values fall within a closed area on a graph with wt % copper on the x-axis and

wt % magnesium on the y-axis, said closed area being bounded by generally straight lines joining the following points:

5 POINT 1 = 0 Cu, 0.6 Mg
 POINT 2 = 4.5 Cu, 0.6 Mg
 POINT 3 = 4.5 Cu, 2.3 Mg
 POINT 4 = 2.0 Cu, 6.0 Mg
 POINT 5 = 0 Cu, 6.0 Mg
 and back to POINT 1.

10 14. The aluminum alloy of Claim 12, wherein the copper and magnesium weight percent values fall within a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, said closed area being bounded by generally straight lines joining the following points:

15 POINT 1 = 0 Cu. 0.6 Mg
 POINT 2 = 4.5 Cu, 0.6 Mg
 POINT 3 = 1.5 Cu, 6.0 Mg
 POINT 4 = 0 Cu, 6.0 Mg
 and back to POINT 1.

20 15. The aluminum alloy of Claim 12, wherein the copper and magnesium weight percent values fall within a closed area on a graph with wt % copper on the x-axis and wt % magnesium on the y-axis, said closed area being bounded by generally straight lines joining the following points:

25 POINT 1 = 0 Cu. 0.6 Mg
 POINT 2 = 4.5 Cu, 0.6 Mg
 POINT 3 = 4.5 Cu, 2.0 Mg
 POINT 4 = 0 Cu, 2.0 Mg
 and back to POINT 1.

30 16. The aluminum alloy of Claim 12, wherein said lithium content is from about 0.25 to 0.99 wt %.

17. The aluminum alloy of Claim 16, wherein
said lithium content is from about 0.25 to
0.95 wt %.

5 18. The aluminum alloy of Claim 17, wherein
said lithium content is from about 0.35 to
0.95 wt %.

19. The aluminum alloy of Claim 12, including
a dispersoid selected from the group consisting
of chromium, vanadium, titanium and zirconium and mixtures
10 thereof in the amount of from about 0.0 to 0.6 wt %.

20. The aluminum alloy of Claim 12, including
a dispersoid selected from the group consisting
of manganese, nickel, iron, hafnium, scandium and mixtures
thereof in the amount of from about 0.0 to 1.0 wt %.

15 21. The aluminum alloy of Claim 12, including
a first dispersoid selected from the group
consisting of chromium, vanadium, titanium, zirconium and
mixtures thereof in the amount of from about 0.0 to 0.6 wt %
and a second dispersoid selected from the group consisting of
20 manganese, nickel, iron, hafnium, scandium and mixtures
thereof in the amount of from about 0.04 to 1.0 wt %.

22. The aluminum alloy of Claim 12, including
other alloying elements selected from the group
consisting of zinc, silver, silicon and mixtures thereof in
25 the amount of from about 0.0 to 2.0 wt %.

23. A damage tolerant aircraft part made from the
alloy of Claim 12.

24. A fuselage section made from the alloy of
Claim 12.

- 19 -

25. A lower wing section made from the alloy of
Claim 12.

647450-6240663

An aluminum-copper-magnesium alloy having ancillary additions of lithium. The alloy composition includes up to about 4.5 wt % copper; from about .6 to 6.0 wt % magnesium; and from about 0.01 to 1.0 wt % lithium.

5

Composition Space Covering Al-Cu-Mg Alloys With Ancillary Li Additions




FIG. 1A




FIG. 1B




FIG. 2




FIG. 3

Fatigue Crack Growth Curves Of Alloy A-T3, Alloy C-T3, Alloy D-T3




FIG. 4

Fatigue Crack Growth Curves Of Alloy A-T39, Alloy C-T39, Alloy D-T39




FIG. 5

Fatigue Crack Growth Curves Of Alloy A-T8, Alloy C-T8, Alloy D-T8




FIG. 6





FIG. 8

FIG. 9



DECLARATION FOR PATENT APPLICATION

As a below named inventor. I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Aluminum-Copper-Magnesium Alloys Having Ancillary Additions of Lithium

the specification of which ☒ is attached hereto

☐ was filed on _____ as Application Serial No. _____
and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)			Priority Claimed	
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

(Appln. Serial No.)	(Filing Date)	(Status—patented, pending, abandoned)
(Appln. Serial No.)	(Filing Date)	(Status—patented, pending, abandoned)

I hereby appoint the following attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Tracey D. Beiriger (Reg. No. 37402), Charles Q. Buckwalter (Reg. No. 32969), Glenn E. Klepac (Reg. No. 26474),
Edward L. Levine (Reg. No. 28097), David W. Pearce-Smith (Reg. No. 31285), Gary P. Topolosky (Reg. No. 31888),
Thomas R. Trempus (Reg. No. 29708)

Address all telephone calls to Charles Q. Buckwalter, Esq. at telephone no. (412)337-2774
Aluminum Company of America
Alcoa Technical Center
100 Technical Drive
Alcoa Center, PA 15069-0001

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under §1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor Roberto J. Rioja

Inventor's signature _____ Date _____
Residence Murrysville, Pennsylvania Citizenship U.S.A.
Post Office Address Aluminum Company of America
Alcoa Technical Center
100 Technical Drive
Alcoa Center, PA 15069-0001

Full name of second joint inventor, if any James T. Staley

Inventor's signature _____ Date _____
City _____ U.S.A. _____

Residence Export, Pennsylvania Citizenship U.S.A.

Full name of third joint inventor, if any Gary H. Bray

Inventor's signature _____ Date _____
City _____ State _____ U.S.A.

Residence Murrysville, PA Citizenship U.S.A.

Post Office Address Aluminum Company of America

Alcoa Technical Center

100 Technical Drive

Alcoa Center, PA 15069-0001

100-443887-100